

Insulated Metallic Substrate CCI SMI FR4 Prepreg




www.ccieurolam.com

GENERAL


SMI is a solution to heat dissipation problems, allowing simple PCB designs. IMS is an alternative to solution such as heat sinks or ceramic substrates, often linked with interconnection difficulties.

SMI can be used in such fields as high voltage applications, power PCBs, coolers for transistors, thyristors, regulators, SMDs, power-LEDs, and in the automotive industry.



STANDARD CONSTRUCTION

ED COPPER Thickness (µm) : 17,5 – 35 – 70 – 105 - 210
FR4 PREPREG Thickness: 117 µm +/- 10%
ALUMINIUM (1050H24) Thickness (mm): 0,8 / 1 / 1,5 / 2 / 3 (others on request)



PROPERTIES

Properties	Test method	Values
Dielectric thermal conductivity	DIN V54462.	0.25 W/K.m
Dielectric Tg	DSC	135°C
Total thickness tolerance		+/-10%.
Break down voltage	IPC TM 650, 2.5.6.2	4.5 kV
Copper peel strength	IPC TM 650, 2.4.8.f	<ul style="list-style-type: none"> • After thermal shock: 1,95 N/mm • At 125 °C: 1,85 N/mm • After process solutions: 1,90 N/mm
Thermal shock resistance	2x20 seconds at 260°C +/-6 °C	Pass
Dielectric volume resistivity	IPC TM 650, 2.5.17.1	<ul style="list-style-type: none"> • C96/35/90: 6,0 x 10⁶ MΩ*cm • Elevated temp. E24/125: 7,2 x 10⁶ MΩ*cm
Dielectric CTI	IEC-112	200 V

Information contained in this technical literature is believed to be accurate and is offered in good faith for the benefit of the consumer but is not binding and is provided without making any representation or warranty, expressed or implied, and without any liability. In as much as CCI Eurolam has no control over the use to which others may put the material, each user of the material is not released of making his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any CCI Eurolam patent or application covering such use or as recommendations for use of such materials in the infringement of any patent

For further information please contact us:

France - Paris - Phone: +33 (0)1 46 74 47 47 - Fax: + 33 (0)1 46 66 63 13 - Email: info@ccieurolam.com
 France - Lyon - Phone: +33 (0)4 72 78 01 90 - Fax: 33 (0)4 78 76 08 91 - Email: info@ccieurolam.com
 Germany - Frankfurt - Phone: + 49 (0)6103 3992-0 - Fax: + 49 (0)6103 3992-29 - Email: info@ccieurolam.de
 UK - Cumbernauld - Phone: +44 793 120 7744 - Fax: + 44 191 422 7228 - Email: ebutchert@ccieurolam.com